



## **Annex G, NSF/ANSI 61 - 2008**

# **Weighted Average Lead Content Evaluation Procedure to a 0.25% Lead Requirement**

April 2009

Attached is a copy of NSF/ANSI 61, Annex G. The annex establishes an evaluation procedure for use when a 0.25% lead content requirement needs to be met in addition to current chemical extraction requirements of the standard.

This annex was developed for the purpose of demonstrating conformance with California's Health & safety Code (Section 116875; commonly referred to as AB1953) and that of other States or jurisdictions with a similar requirement.

The annex is provided here for informational purposes only. NSF/ANSI Standard 61 in its entirety should be used when evaluating products for compliance.

## Annex G (normative)

### Weighed average lead content evaluation procedure to a 0.25% lead requirement

#### G.1 General

This is an optional evaluation method for products that need to meet a 0.25% weighted average lead content standard. Certification of products to this annex shall be noted in the certification listing.

Products must first comply with the full requirements of NSF/ANSI 61 in order to be deemed compliant to this section.

#### G.2 General Evaluation Protocol

##### G.2.1 All components $\leq 0.25\%$

If each component of a product has a wetted surface with a verifiable lead content of not more than 0.25%, then the product is considered compliant with the requirements of this annex and no further evaluation is required.

##### G.2.2 Some components $\geq 0.25\%$

If some wetted components of a product contain more than 0.25% lead, then the weighted lead content shall be calculated according to G.3 to determine compliance with the requirements of this annex.

#### G.3 Weighted average lead content calculation

The weighted average lead content of the product can be calculated using information that is provided as part of the manufacturer's submittal under 3.2. For internal threaded products, the wetted surface area shall include 25% of the threaded area(s).

All of the wetted surfaces are to be included in the weighted average lead content calculation, not just those surfaces that contain lead. If the weighted average lead content is greater than 0.25%, the manufacturer can replace wetted components containing lead with non-lead materials until the weighted average lead content is less than or equal to 0.25%.

The results of the weighted average lead calculation shall be rounded to two decimal places prior to determination of compliance with the requirements of this annex.

##### G.3.1 Formula for determining weighted average lead content

The following formulation shall be used when calculating the weighted average lead content of products:

$$WLC = \sum_{c=1}^n \left( LC_c \times \left[ \frac{WSA_c}{WSA_t} \right] \right)$$

where;

WLC = weighted average lead content of product  
 LC<sub>c</sub> = percentage lead content of component  
 WSA<sub>c</sub> = wetted surface area of component  
 WSA<sub>t</sub> = total wetted surface area of all components  
 n = number of wetted components in product

NOTE – An example calculation of the weighted average lead content of a product is provided in section G.5

## G.4 Lead content of water contact surfaces

The lead content of the material specification used to produce wetted components shall be used to determine compliance with this standard. For lead contents of materials that are provided as a range, the maximum content of the range shall be used.

**G.4.1 Use of Liners:** When lead-bearing surfaces have been excluded from water contact by use of a rigid liner (e.g. plastic sleeve) sealed with a permanent barrier, the lead content of the liner shall be used.

**G.4.2 Use of coatings:** When coatings are used, the lead content of the coated substrate shall be used in the calculation of weighted average lead content.

**G.4.3 Use of lead removal technologies:** For components where the wetted surface areas have been treated with a lead removal technology, the percent lead composition shall be based on the material used to manufacture the component prior to application of the surface treatment.

## G.5 Example weighted average lead content calculation

The following is an example of how this weighted average lead content calculation is conducted.

1. Identify those components of the faucet that water flows through and comes into contact with during the normal operation (wetted components).
2. Use the percentage of lead content within each component (supplied by the component manufacturer or supplier). Table G1 – column 4 provides the lead content for each of the wetted components.
3. Determine the percent of total wetted surface area represented in each component using the part specifications.
  - a. The *wetted surface area* of each component that comes into direct contact with water is required under 3.2 (to be provided by the manufacturer). Table G1 - column 2 shows the *wetted surface area* of the subject faucet.
  - b. Add the areas of the wetted surface for each component together: this is the *total wetted surface area of the faucet*.
  - c. For each component, divide the *area of its wetted surface* by the *total wetted surface area of the faucet (times 100)*: this is the percent of total wetted surface area of each component (see Table G1 – column 3).

$$\text{Percent wetted surface area} = \frac{\text{Wetted surface area of component}}{\text{Total wetted surface area}} \times 100$$

4. For each component, multiply the percentage of lead content by the percent of total wetted surface area of that component: this is the *contributing percent lead for each component* (see Table G1 – column 5).

$$\text{Contributing percent lead} = (\text{Percent wetted surface area} / 100) \times (\text{Percent lead content} / 100) \times 100$$

5. Calculate the weighted average lead content of the faucet by totaling the *contributing percent lead for the components that make up the wetted surface* of the faucet (Table G1 – column 5). For the faucet to be in compliance with this annex, this total must be no more than 0.25%.

**Table G1. Example of weighted average lead content calculations.**

1	2	3	4	5
Component No.	Wetted surface area <sup>1</sup> (total = 61.94 in <sup>2</sup> )	% wetted surface area (total = 100%)	% lead content	Contributing % lead
1	17.31	27.95	0.05	0.01
2	1.15	1.85	2.86	0.05
3	4.99	8.05	0.23	0.02
4	18.25	29.46	0.05	0.01
5	11.14	17.98	0	0.00
6	4.02	6.49	0	0.00
7	1.09	1.75	1.30	0.02
8	0.54	0.87	0	0.00
9	0.91	1.48	2.54	0.04
10	0.76	1.23	0	0.00
11	1.02	1.64	2.54	0.04
12	0.35	0.56	2.54	0.01
13	0.43	0.69	2.54	0.02
Weighted average lead content =				0.23% (in compliance)

NOTE – Calculated data for each component in columns 3 and 5 show in this table with two decimal places to increase readability. When the calculation is performed, rounding to 2 decimal places is only performed on the final result.